




Carbide end mills with TiAlN coating

EPS • EPL SERIES

Volume 2



FEATURES: EPS-LN-EBD • EPS-CPR



1 EPS-LN-EBD Ball nose
EPS-CPR with corner radius



2 For hardened steels up to 65 HRC

3 TiAlN coating




GEOMETRICAL ACCURACY

TYPE	TOLERANCE
EPL-CPR	+/- 0.005mm
EPL-LN-EBD	+/- 0.005mm
EPS-CPR	+/- 0.005mm
EPS-LN-EBD	+/- 0.005mm




EPS-LN-EBD NEW SIZES

Milling | Solid carbide



- Carbide end mill with TiAlN coating
- For hardened steels up to 65 HRC
- 2 flutes, long neck, ball nose




EDP	Z	D	R	l1	L	l	d	d1	θk	Le (α) 0,5°	Le (α) 1°	Le (α) 1,5°	Le (α) 2°	Le (α) 2,5°	Le (α) 3°	Price
NEW EP01951201	2	0,2	0,1	0,5	45	0,16	4	0,18	14,16	0,53	0,55	0,57	0,59	0,61	0,63	
NEW EP01951202	2	0,2	0,1	0,75	45	0,16	4	0,18	13,72	0,79	0,82	0,85	0,88	0,91	0,94	
NEW EP01951205	2	0,2	0,1	1	45	0,16	4	0,18	13,31	1,05	1,09	1,13	1,17	1,21	1,26	
NEW EP01951203	2	0,2	0,1	1,25	45	0,16	4	0,18	12,92	1,31	1,36	1,41	1,46	1,51	1,57	
NEW EP01951204	2	0,2	0,1	1,75	45	0,16	4	0,18	12,21	1,83	1,9	1,96	2,03	2,11	2,19	
NEW EP01951206	2	0,2	0,1	2	45	0,16	4	0,18	11,88	2,09	2,16	2,24	2,32	2,4	2,5	
EP01950001	2	0,3	0,15	0,6	45	0,16	4	0,28	14,03°	0,63	0,65	0,68	0,7	0,72	0,75	
EP01950002	2	0,3	0,15	1	45	0,24	4	0,28	13,34°	1,05	1,09	1,12	1,16	1,2	1,24	
EP01950003	2	0,3	0,15	1,5	45	0,24	4	0,28	12,57°	1,57	1,63	1,68	1,74	1,8	1,87	
NEW EP01950004	2	0,3	0,15	2	45	0,24	4	0,28	11,87	2,09	2,16	2,23	2,31	2,4	2,49	
NEW EP01950006	2	0,3	0,15	3	45	0,24	4	0,28	10,69	3,13	3,23	3,34	3,46	3,59	3,73	
EP01950101	2	0,4	0,2	0,8	45	0,3	4	0,37	13,74°	0,83	0,86	0,88	0,91	0,94	0,97	
EP01950102	2	0,4	0,2	1	45	0,3	4	0,37	13,39°	1,04	1,07	1,11	1,14	1,18	1,22	
EP01950103	2	0,4	0,2	1,5	45	0,3	4	0,37	12,59°	1,56	1,61	1,66	1,72	1,77	1,84	
EP01950104	2	0,4	0,2	2	45	0,3	4	0,37	11,88°	2,08	2,14	2,21	2,29	2,37	2,46	
NEW EP01950105	2	0,4	0,2	2,5	45	0,3	4	0,37	11,24	2,6	2,68	2,77	2,87	2,97	3,08	
NEW EP01950106	2	0,4	0,2	3	45	0,3	4	0,37	10,67	3,11	3,21	3,32	3,44	3,57	3,7	
NEW EP01950107	2	0,4	0,2	3,5	45	0,3	4	0,37	10,15	3,63	3,75	3,88	4,02	4,16	4,33	
NEW EP01950108	2	0,4	0,2	4	45	0,3	4	0,37	9,68	4,15	4,28	4,43	4,59	4,76	4,95	
EP01950201	2	0,5	0,25	1	45	0,4	4	0,45	13,45°	1,03	1,06	1,09	1,12	1,15	1,19	
EP01950202	2	0,5	0,25	1,5	45	0,4	4	0,45	12,62°	1,55	1,59	1,64	1,69	1,75	1,81	
EP01950203	2	0,5	0,25	2	45	0,4	4	0,45	11,89°	2,06	2,13	2,2	2,27	2,35	2,43	
EP01950204	2	0,5	0,25	2,5	45	0,4	4	0,45	11,23°	2,58	2,66	2,75	2,84	2,94	3,05	
NEW EP01950208	2	0,5	0,25	3	45	0,4	4	0,45	10,65	3,1	3,2	3,3	3,42	3,54	3,68	
EP01950205	2	0,5	0,25	3,5	45	0,4	4	0,45	10,12°	3,61	3,73	3,86	3,99	4,14	4,3	
EP01950206	2	0,5	0,25	4	45	0,4	4	0,45	9,64°	4,13	4,27	4,41	4,57	4,74	4,92	
NEW EP01950209	2	0,5	0,25	5	45	0,4	4	0,45	8,8	5,17	5,34	5,52	5,72	5,93	6,16	
EP01950207	2	0,5	0,25	6	45	0,4	4	0,45	8,1°	6,2	6,41	6,63	6,87	7,13	7,41	
EP01950301	2	0,6	0,3	1,2	45	0,5	4	0,55	13,14°	1,24	1,27	1,3	1,34	1,38	1,43	
EP01950302	2	0,6	0,3	2	45	0,5	4	0,55	11,88°	2,06	2,12	2,19	2,26	2,34	2,42	
NEW EP01950307	2	0,6	0,3	2,5	45	0,5	4	0,55	11,21	2,58	2,66	2,74	2,84	2,94	3,04	
EP01950303	2	0,6	0,3	3	45	0,5	4	0,55	10,61°	3,1	3,19	3,3	3,41	3,53	3,66	
EP01950304	2	0,6	0,3	4	45	0,5	4	0,55	9,58°	4,13	4,26	4,41	4,56	4,73	4,91	
EP01950305	2	0,6	0,3	5	45	0,5	4	0,55	8,73°	5,16	5,33	5,51	5,71	5,92	6,15	
NEW EP01950306	2	0,6	0,3	6	45	0,5	4	0,55	8,02	6,2	6,4	6,62	6,86	7,12	7,39	
NEW EP01950308	2	0,6	0,3	8	45	0,5	4	0,55	6,89	8,26	8,54	8,84	9,16	9,51	9,88	
EP01950401	2	0,8	0,4	2	45	0,6	4	0,75	11,86°	2,06	2,12	2,18	2,25	2,32	2,4	
EP01950402	2	0,8	0,4	3	45	0,6	4	0,75	10,52°	3,09	3,19	3,29	3,4	3,51	3,64	
EP01950403	2	0,8	0,4	4	45	0,6	4	0,75	9,45°	4,13	4,26	4,4	4,55	4,71	4,88	
EP01950404	2	0,8	0,4	5	45	0,6	4	0,75	8,58°	5,16	5,33	5,5	5,7	5,9	6,13	
NEW EP01950405	2	0,8	0,4	6	45	0,6	4	0,75	7,85	6,19	6,4	6,61	6,85	7,1	7,37	
NEW EP01950406	2	0,8	0,4	10	45	0,6	4	0,75	5,86	10,33	10,67	11,05	11,45	11,88	12,34	
EP01950501	2	1	0,5	2	45	0,8	4	0,95	11,84°	2,06	2,11	2,17	2,23	2,3	2,37	
EP01950502	2	1	0,5	3	45	0,8	4	0,95	10,43°	3,09	3,18	3,28	3,38	3,49	3,62	
EP01950503	2	1	0,5	4	45	0,8	4	0,95	9,32°	4,12	4,25	4,39	4,53	4,69	4,86	

Milling | Solid carbide




EPS-LN-EBD NEW SIZES

Milling | Solid carbide



- Carbide end mill with TiAlN coating
- For hardened steels up to 65 HRC
- 2 flutes, long neck, ball nose




EDP	Z	D	R	l1	L	l	d	d1	Øk	Le (α) 0,5°	Le (α) 1°	Le (α) 1,5°	Le (α) 2°	Le (α) 2,5°	Le (α) 3°	Price
NEW EP01950508	2	1	0,5	5	45	0,8	4	0,95	8,41	5,16	5,32	5,49	5,68	5,88	6,1	
EP01950504	2	1	0,5	6	45	0,8	4	0,95	7,67°	6,19	6,39	6,6	6,83	7,08	7,35	
NEW EP01950509	2	1	0,5	7	45	0,8	4	0,95	7,05	7,22	7,46	7,71	7,98	8,27	8,59	
EP01950505	2	1	0,5	8	45	0,8	4	0,95	6,52°	8,26	8,53	8,82	9,13	9,47	9,83	
EP01950506	2	1	0,5	10	45	0,8	4	0,95	5,66°	10,33	10,67	11,04	11,43	11,86	12,32	
EP01950507	2	1	0,5	12	45	0,8	4	0,95	5,01°	12,39	12,81	13,25	13,73	14,25	14,81	
NEW EP01950510	2	1	0,5	14	50	0,8	4	0,95	4,49	14,46	14,95	15,47	16,03	16,64	17,29	
NEW EP01950511	2	1	0,5	16	50	0,8	4	0,95	4,06	16,53	17,09	17,69	18,33	19,03	19,78	
NEW EP01951301	2	1,2	0,6	2,4	45	1	4	1,15	11,03	2,51	2,61	2,7	2,78	2,87	2,96	
NEW EP01951302	2	1,2	0,6	4	45	1	4	1,15	9,07	4,19	4,34	4,48	4,62	4,78	4,95	
NEW EP01951303	2	1,2	0,6	6	45	1	4	1,15	7,41	6,27	6,48	6,69	6,92	7,17	7,44	
NEW EP01951304	2	1,2	0,6	8	45	1	4	1,15	6,26	8,35	8,62	8,91	9,22	9,56	9,93	
EP01950601	2	1,5	0,75	3	45	1,2	4	1,45	10,01°	3,13	3,25	3,35	3,45	3,56	3,67	
EP01950602	2	1,5	0,75	4	45	1,2	4	1,45	8,8°	4,18	4,33	4,46	4,6	4,75	4,92	
EP01950603	2	1,5	0,75	6	45	1,2	4	1,45	7,08°	6,27	6,47	6,68	6,9	7,14	7,4	
EP01950604	2	1,5	0,75	8	45	1,2	4	1,45	5,92°	8,34	8,61	8,9	9,2	9,53	9,89	
NEW EP01950606	2	1,5	0,75	10	45	1,2	4	1,45	5,09	10,41	10,75	11,11	11,5	11,92	12,38	
EP01950605	2	1,5	0,75	12	45	1,2	4	1,45	4,46°	12,48	12,89	13,33	13,8	14,31	14,86	
NEW EP01950607	2	1,5	0,75	16	50	1,2	4	1,45	3,57	16,62	17,17	17,76	18,4	19,09	19,83	
NEW EP01950608	2	1,5	0,75	20	55	1,2	4	1,45	2,98	20,75	21,45	22,19	23	23,87	-	
NEW EP01951401	2	1,6	0,8	8	45	1,3	4	1,55	5,8	8,34	8,61	8,89	9,19	9,52	9,88	
NEW EP01951402	2	1,6	0,8	12	45	1,3	4	1,55	4,34	12,48	12,89	13,32	13,79	14,3	14,85	
EP01950701	2	2	1	4	45	1,6	4	1,95	7,87°	4,18	4,33	4,46	4,6	4,75	4,92	
EP01950702	2	2	1	6	45	1,6	4	1,95	6,19°	6,27	6,47	6,68	6,9	7,14	7,4	
EP01950703	2	2	1	8	45	1,6	4	1,95	5,1°	8,34	8,61	8,9	9,2	9,53	9,89	
EP01950704	2	2	1	10	45	1,6	4	1,95	4,33°	10,41	10,75	11,11	11,5	11,92	12,38	
EP01950705	2	2	1	12	45	1,6	4	1,95	3,77°	12,48	12,89	13,33	13,8	14,31	14,86	
EP01950706	2	2	1	14	50	1,6	4	1,95	3,33°	14,55	15,03	15,55	16,1	16,7	17,35	
EP01950707	2	2	1	16	50	1,6	4	1,95	2,98°	16,62	17,17	17,76	18,4	19,09	19,83	
NEW EP01950708	2	2	1	20	55	1,6	4	1,95	2,47	21,05	21,78	22,54	23,34	-	-	
NEW EP01950709	2	2	1	25	65	1,6	4	1,95	2,03	26,24	27,13	28,08	29,09	-	-	
NEW EP01950710	2	2	1	30	70	1,6	4	1,95	1,73	31,42	32,48	33,62	-	-	-	
EP01950801	2	2,5	1,25	10	45	2	4	2,35	3,63°	10,46	10,85	11,21	11,59	11,99	12,43	
NEW EP01950802	2	2,5	1,25	20	55	2	4	2,35	1,97	20,87	21,56	22,3	-	-	-	
EP01950901	2	3	1,5	6	50	2,4	6	2,85	8,17°	6,25	6,49	6,72	6,95	7,17	7,4	
EP01950902	2	3	1,5	8	50	2,4	6	2,85	6,88°	8,35	8,67	8,97	9,25	9,55	9,88	
EP01950903	2	3	1,5	10	50	2,4	6	2,85	5,94°	10,44	10,83	11,19	11,55	11,94	12,37	
EP01950904	2	3	1,5	12	55	2,4	6	2,85	5,22°	12,53	12,98	13,4	13,85	14,33	14,86	
NEW EP01950908	2	3	1,5	14	55	2,4	6	2,85	4,66	14,62	15,13	15,62	16,15	16,72	17,34	
EP01950905	2	3	1,5	15	55	2,4	6	2,85	4,42°	15,66	16,2	16,73	17,3	17,92	18,59	
EP01950906	2	3	1,5	16	55	2,4	6	2,85	4,21°	16,7	17,26	17,84	18,45	19,11	19,83	
EP01950907	2	3	1,5	20	60	2,4	6	2,85	3,52°	20,86	21,54	22,27	23,05	23,89	24,8	
NEW EP01950909	2	3	1,5	25	65	2,4	6	2,85	2,92	26,04	26,89	27,81	28,8	29,86	-	
NEW EP01950910	2	3	1,5	30	70	2,4	6	2,85	2,5	31,2	32,24	33,35	34,55	-	-	
NEW EP01951501	2	3,5	1,75	20	60	2,8	6	3,35	3,08	20,85	21,53	22,24	23,01	23,84	24,74	

Milling | Solid carbide




EPS-LN-EBD NEW SIZES

Milling | Solid carbide



- Carbide end mill with TiAlN coating
- For hardened steels up to 65 HRC
- 2 flutes, long neck, ball nose




EDP	Z	D	R	l1	L	l	d	d1	θk	Le (α) 0,5°	Le (α) 1°	Le (α) 1,5°	Le (α) 2°	Le (α) 2,5°	Le (α) 3°	Price
EP01951001	2	4	2	8	55	3,2	6	3,85	5,67°	8,33	8,63	8,91	9,18	9,46	9,77	
EP01951002	2	4	2	10	60	3,2	6	3,85	4,74°	10,42	10,79	11,13	11,48	11,85	12,25	
EP01951003	2	4	2	12	60	3,2	6	3,85	4,07°	12,51	12,95	13,35	13,78	14,24	14,74	
NEW EP01951006	2	4	2	15	60	3,2	6	3,85	3,36	15,64	16,16	16,67	17,23	17,82	18,47	
EP01951004	2	4	2	16	60	3,2	6	3,85	3,18°	16,68	17,23	17,78	18,38	19,02	19,71	
EP01951005	2	4	2	20	65	3,2	6	3,85	2,6°	20,84	21,51	22,22	22,98	23,8	-	
NEW EP01951007	2	4	2	25	70	3,2	6	3,85	2,12	26,02	26,86	27,76	28,72	-	-	
NEW EP01951601	2	5	2,5	20	70	4	6	4,85	1,46	20,82	21,47	-	-	-	-	
NEW EP01951602	2	5	2,5	40	90	4	6	4,85	0,72	41,51	-	-	-	-	-	
EP01951101	2	6	3	12	60	4,8	6	5,85	-	-	-	-	-	-	-	
NEW EP01951102	2	6	3	20	70	4,8	6	5,85	-	-	-	-	-	-	-	
NEW EP01951103	2	6	3	25	70	4,8	6	5,85	-	-	-	-	-	-	-	
NEW EP01951104	2	6	3	30	80	4,8	6	5,85	-	-	-	-	-	-	-	

Milling | Solid carbide



EPS-CPR

Milling | Solid carbide



- Carbide end mill with TiAlN coating
- For hardened steels up to 65 HRC
- 2 flutes, long and pencil neck, corner radius




EDP	Z	D	R	l1	l	l2	d	d1	L	Price
EP01960001	2	1	0,05	4	0,8	9,69	4	0,94	50	
EP01960002	2	1	0,1	4	0,8	9,69	4	0,94	50	
EP01960003	2	1	0,1	6	0,8	11,69	4	0,94	50	
EP01960004	2	1	0,2	6	0,8	11,69	4	0,94	50	
EP01960005	2	1	0,3	4	0,8	9,69	4	0,94	50	
EP01960101	2	1,5	0,2	6	1,2	10,75	4	1,43	50	
EP01960102	2	1,5	0,2	10	1,2	14,75	4	1,43	50	
EP01960103	2	1,5	0,2	16	1,2	20,75	4	1,43	50	
EP01960104	2	1,5	0,3	6	1,2	10,75	4	1,43	50	
EP01960201	2	2	0,1	8	1,6	11,82	4	1,92	50	
EP01960202	2	2	0,2	10	1,6	13,82	4	1,92	50	
EP01960203	2	2	0,2	12	1,6	15,82	4	1,92	50	
EP01960204	2	2	0,3	8	1,6	11,82	4	1,92	50	
EP01960205	2	2	0,5	8	1,6	11,82	4	1,92	50	
EP01960206	2	2	0,5	12	1,6	15,82	4	1,92	50	
EP01960301	2	3	0,2	8	2,5	13,87	6	2,85	60	
EP01960302	2	3	0,3	12	2,5	17,87	6	2,85	60	
EP01960303	2	3	0,3	16	2,5	21,87	6	2,85	60	
EP01960401	4	4	0,2	16	4	20,01	6	3,84	60	
EP01960402	4	4	0,2	20	4	24,01	6	3,84	60	
EP01960403	4	4	0,5	16	4	20,01	6	3,84	60	




EPL-LN-EBD

Milling | Solid carbide



- Carbide end mill with TiAlN coating
- For general applications
- 2 flutes, long neck, ball nose




EDP	Z	D	R	l1	d	d1	l	L	θk	Le (α) 0,5°	Le (α) 1°	Le (α) 1,5°	Le (α) 2°	Le (α) 2,5°	Le (α) 3°	Price
EP48165001	2	0,3	0,15	0,5	4	0,28	0,24	45	14,22	0,52	0,54	0,56	0,58	0,6	0,62	
EP48165002	2	0,3	0,15	1	4	0,28	0,24	45	13,34	1,05	1,09	1,12	1,16	1,2	1,24	
EP48165003	2	0,4	0,2	1	4	0,37	0,3	45	13,39	1,04	1,07	1,11	1,14	1,18	1,22	
EP48165004	2	0,4	0,2	2	4	0,37	0,3	45	11,88	2,08	2,14	2,21	2,29	2,37	2,46	
EP48165005	2	0,5	0,25	1	4	0,45	0,4	45	13,45	1,03	1,06	1,09	1,12	1,15	1,19	
EP48165006	2	0,5	0,25	2	4	0,45	0,4	45	11,89	2,06	2,13	2,2	2,27	2,35	2,43	
EP48165007	2	0,5	0,25	3	4	0,45	0,4	45	10,65	3,1	3,2	3,3	3,42	3,54	3,68	
EP48165008	2	0,5	0,25	4	4	0,45	0,5	45	9,64	4,13	4,27	4,41	4,57	4,74	4,92	
EP48165009	2	0,6	0,3	1	4	0,55	0,5	45	13,49	1,03	1,05	1,08	1,11	1,14	1,18	
EP48165010	2	0,6	0,3	2	4	0,55	0,5	45	11,88	2,06	2,12	2,19	2,26	2,34	2,42	
EP48165011	2	0,6	0,3	3	4	0,55	0,5	45	10,61	3,1	3,19	3,3	3,41	3,53	3,66	
EP48165012	2	0,6	0,3	4	4	0,55	0,5	45	9,58	4,13	4,26	4,41	4,56	4,73	4,91	
EP48165013	2	0,6	0,3	6	4	0,55	0,5	45	8,02	6,2	6,4	6,62	6,86	7,12	7,39	
EP48165014	2	0,8	0,4	2	4	0,75	0,6	45	11,86	2,06	2,12	2,18	2,25	2,32	2,4	
EP48165015	2	0,8	0,4	4	4	0,75	0,6	45	9,45	4,13	4,26	4,4	4,55	4,71	4,88	
EP48165016	2	0,8	0,4	6	4	0,75	0,6	45	7,85	6,19	6,4	6,61	6,85	7,1	7,37	
EP48165017	2	1	0,5	2,5	4	0,95	0,8	45	11,09	2,57	2,64	2,72	2,81	2,9	3	
EP48165018	2	1	0,5	3	4	0,95	0,8	45	10,43	3,09	3,18	3,28	3,38	3,49	3,62	
EP48165019	2	1	0,5	4	4	0,95	0,8	45	9,32	4,12	4,25	4,39	4,53	4,69	4,86	
EP48165020	2	1	0,5	5	4	0,95	0,8	45	8,41	5,16	5,32	5,49	5,68	5,88	6,1	
EP48165021	2	1	0,5	6	4	0,95	0,8	45	7,67	6,19	6,39	6,6	6,83	7,08	7,35	
EP48165022	2	1	0,5	8	4	0,95	0,8	45	6,52	8,26	8,53	8,82	9,13	9,47	9,83	
EP48165023	2	1	0,5	10	4	0,95	0,8	45	5,66	10,33	10,67	11,04	11,43	11,86	12,32	
EP48165024	2	1	0,5	12	4	0,95	0,8	45	5,01	12,39	12,81	13,25	13,73	14,25	14,81	
EP48165025	2	1,5	0,75	4	4	1,45	1,2	45	8,8	4,18	4,33	4,46	4,6	4,75	4,92	
EP48165026	2	1,5	0,75	8	4	1,45	1,2	45	5,92	8,34	8,61	8,9	9,2	9,53	9,89	
EP48165027	2	2	1	6	4	1,95	1,6	45	6,19	6,36	6,67	6,96	7,23	7,49	7,76	
EP48165028	2	2	1	8	4	1,95	1,6	45	5,1	8,48	8,87	9,22	9,55	9,88	10,24	
EP48165029	2	2	1	10	4	1,95	1,6	45	4,33	10,59	11,05	11,45	11,85	12,27	12,73	
EP48165030	2	2	1	12	4	1,95	1,6	45	3,77	12,69	13,21	13,67	14,15	14,66	15,22	
EP48165031	2	2	1	14	4	1,95	1,6	50	3,33	14,78	15,36	15,89	16,45	17,05	17,7	
EP48165032	2	2	1	16	4	1,95	1,6	50	2,98	16,88	17,51	18,1	18,75	19,44	-	
EP48165033	2	2	1	20	4	1,95	1,6	55	2,47	21,05	21,78	22,54	23,34	-	-	
EP48165034	2	2	1	25	4	1,95	1,6	65	2,03	26,24	27,13	28,08	29,09	-	-	
EP48165035	2	3	1,5	8	6	2,85	2,4	50	6,88	8,35	8,67	8,97	9,25	9,55	9,88	
EP48165036	2	3	1,5	10	6	2,85	2,4	50	5,94	10,44	10,83	11,19	11,55	11,94	12,37	
EP48165037	2	3	1,5	16	6	2,85	2,4	55	4,21	16,7	17,26	17,84	18,45	19,11	19,83	
EP48165038	2	3	1,5	20	6	2,85	2,4	60	3,52	20,86	21,54	22,27	23,05	23,89	24,8	
EP48165039	2	4	2	10	6	3,85	3,2	60	4,74	10,42	10,79	11,13	11,48	11,85	12,25	
EP48165040	2	4	2	16	6	3,85	3,2	60	3,18	16,68	17,23	17,78	18,38	19,02	19,71	
EP48165041	2	4	2	20	6	3,85	3,2	65	2,6	20,84	21,51	22,22	22,98	23,8	-	
EP48165042	2	4	2	25	6	3,85	3,2	70	2,12	26,02	26,86	27,76	28,72	-	-	
EP48165043	2	4	2	30	6	3,85	3,2	80	1,79	31,19	32,21	33,3	-	-	-	
EP48165044	2	6	3	10	6	5,85	6	60	-	-	-	-	-	-	-	
EP48165045	2	6	3	12	6	5,85	6	60	-	-	-	-	-	-	-	
EP48165046	2	6	3	20	6	5,85	6	70	-	-	-	-	-	-	-	
EP48165047	2	6	3	30	6	5,85	6	80	-	-	-	-	-	-	-	

Milling | Solid carbide



EPL-CPR

Milling | Solid carbide



- Carbide end mills with TiAlN coating
- For general applications
- 2 flutes, long neck, corner radius




EDP	Z	D	R	α°	L	l	l1	d	Price
W0901001	2	2	0,5	0,9	65	6	20	6	
W0901002	2	2	0,5	0,9	70	6	30	6	
W0901003	2	3	0,5	0,9	65	8	20	6	
W0901004	2	3	0,5	0,9	70	8	30	6	
W0901005	2	3	0,5	0,9	80	8	40	6	
W0901034	2	3	0,5	1,4	65	8	20	6	
W0901035	2	3	0,5	1,4	70	8	30	6	
W0901036	2	3	1	1,4	65	8	20	6	
W0901037	2	3	1	1,4	70	8	30	6	
W0901038	2	3	1	1,4	80	8	40	6	
W0901006	2	3	1	0,9	65	8	20	6	
W0901007	2	3	1	0,9	70	8	30	6	
W0901008	2	3	1	0,9	80	8	40	6	
W0901009	2	4	0,5	0,9	90	10	30	8	
W0901010	2	4	0,5	0,9	100	10	40	8	
W0901011	2	4	0,5	0,9	120	10	50	8	
W0901039	2	4	0,5	1,4	100	10	30	8	
W0901040	2	4	0,5	1,4	100	10	40	8	
W0901041	2	4	1	1,4	100	10	30	8	
W0901042	2	4	1	1,4	100	10	40	8	
W0901012	2	4	1	0,9	90	10	30	8	
W0901013	2	4	1	0,9	100	10	40	8	
W0901014	2	4	1	0,9	120	10	50	8	
W0901015	2	4	1	0,9	120	10	60	8	
W0901018	2	6	0,5	0,9	120	12	50	10	
W0901019	2	6	0,5	0,9	120	12	60	10	
W0901020	2	6	0,5	0,9	130	12	70	10	
W0901021	2	6	1	0,9	120	12	50	10	
W0901022	2	6	1	0,9	120	12	60	10	
W0901023	2	6	1	0,9	130	12	70	10	
W0901024	2	6	1	0,9	130	12	80	10	
W0901027	2	8	0,5	0,9	150	20	60	10	
W0901028	2	8	0,5	0,9	150	20	80	10	
W0901029	2	8	1	0,9	150	20	60	10	
W0901030	2	8	1	0,9	150	20	80	10	
W0901033	2	8	2	0,9	150	20	80	10	



EPL-CPR

Milling | Solid carbide



- Carbide end mills with TiAlN coating
- For general applications
- 2 flutes, long neck, corner radius



EDP	Z	D	R	l1	d	d1	l	L	Price
EP48166001	2	1	0,1	4	4	0,95	0,8	50	
EP48166002	2	1	0,1	6	4	0,95	0,8	50	
EP48166003	2	1	0,1	8	4	0,95	0,8	50	
EP48166004	2	1	0,2	4	4	0,95	0,8	50	
EP48166005	2	1	0,2	6	4	0,95	0,8	50	
EP48166006	2	1	0,2	8	4	0,95	0,8	50	
EP48166007	2	1	0,2	10	4	0,95	0,8	50	
EP48166008	2	1	0,3	4	4	0,95	0,8	50	
EP48166009	2	1	0,3	6	4	0,95	0,8	50	
EP48166010	2	1	0,3	8	4	0,95	0,8	50	
EP48166011	2	1	0,3	10	4	0,95	0,8	50	
EP48166012	2	2	0,2	6	4	1,95	1,6	50	
EP48166013	2	2	0,2	8	4	1,95	1,6	50	
EP48166014	2	2	0,2	10	4	1,95	1,6	50	
EP48166015	2	2	0,2	12	4	1,95	1,6	50	
EP48166016	2	2	0,2	16	4	1,95	1,6	50	
EP48166017	2	2	0,5	6	4	1,95	1,6	50	
EP48166018	2	2	0,5	8	4	1,95	1,6	50	
EP48166019	2	2	0,5	10	4	1,95	1,6	50	
EP48166020	2	2	0,5	12	4	1,95	1,6	50	
EP48166021	2	2	0,5	16	4	1,95	1,6	50	
EP48166022	2	3	0,2	6	6	2,85	2,5	60	
EP48166023	2	3	0,2	8	6	2,85	2,5	60	
EP48166024	2	3	0,2	10	6	2,85	2,5	60	
EP48166025	2	3	0,2	12	6	2,85	2,5	60	
EP48166026	2	3	0,2	16	6	2,85	2,5	60	
EP48166027	2	3	0,5	6	6	2,85	2,5	60	
EP48166028	2	3	0,5	8	6	2,85	2,5	60	
EP48166029	2	3	0,5	10	6	2,85	2,5	60	
EP48166030	2	3	0,5	12	6	2,85	2,5	60	
EP48166031	2	3	0,5	16	6	2,85	2,5	60	
EP48166032	2	4	0,5	12	6	3,85	4	60	
EP48166033	2	4	0,5	16	6	3,85	4	60	
EP48166034	2	4	0,5	20	6	3,85	4	60	
EP48166035	2	4	1	10	6	3,85	4	60	
EP48166036	2	4	1	12	6	3,85	4	60	
EP48166037	2	4	1	16	6	3,85	4	60	
EP48166038	2	4	1	20	6	3,85	4	60	
EP48166039	2	6	0,5	12	6	5,85	6	70	
EP48166040	2	6	0,5	16	6	5,85	6	70	
EP48166041	2	6	0,5	20	6	5,85	6	70	
EP48166042	2	6	0,5	25	6	5,85	6	70	



CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPS-LN-EBD

High speed milling

Vc		C≤0,2% - GG				~30 HRC				30~38 HRC			
R	l1 (mm)	120 (m/min)				110 (m/min)				100 (m/min)			
		S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)
1,5	6	41.500	6.200	0,15	0,3	41.500	6.200	0,15	0,3	41.500	6.200	0,15	0,3
1,5	8	30.000	4.500	0,15	0,3	30.000	4.500	0,15	0,3	30.000	4.200	0,15	0,3
1,5	10	25.000	3.800	0,15	0,3	25.000	3.800	0,15	0,3	25.000	3.600	0,15	0,3
1,5	12	20.000	3.000	0,15	0,3	20.000	3.000	0,15	0,3	20.000	2.800	0,15	0,3
1,5	14	18.000	2.700	0,15	0,3	18.000	2.700	0,15	0,3	18.000	2.500	0,15	0,3
1,5	15	16.000	2.400	0,1	0,3	16.000	2.400	0,1	0,3	16.000	2.200	0,1	0,3
1,5	16	16.000	2.000	0,1	0,2	16.000	2.000	0,1	0,2	16.000	1.900	0,1	0,2
1,5	20	14.000	1.800	0,1	0,2	14.000	1.800	0,1	0,2	14.000	1.700	0,1	0,2
1,5	25	12.000	1.200	0,05	0,1	12.000	1.200	0,05	0,1	12.000	1.100	0,05	0,1
1,5	30	10.000	800	0,03	0,05	10.000	800	0,03	0,05	10.000	760	0,03	0,05
1,75	20	16.000	2.700	0,1	0,2	16.000	2.700	0,1	0,2	16.000	2.500	0,1	0,2
2	8	31.000	5.700	0,2	0,5	31.000	5.700	0,2	0,5	31.000	5.700	0,2	0,5
2	10	25.000	4.500	0,2	0,5	25.000	4.500	0,2	0,5	25.000	4.200	0,2	0,5
2	12	20.000	4.000	0,2	0,5	20.000	4.000	0,2	0,5	20.000	3.000	0,2	0,5
2	15	20.000	3.600	0,2	0,5	20.000	4.000	0,2	0,5	20.000	3.000	0,2	0,5
2	16	18.000	3.200	0,2	0,5	18.000	3.200	0,2	0,5	18.000	3.000	0,2	0,5
2	20	16.000	2.800	0,2	0,4	16.000	2.800	0,2	0,4	16.000	2.600	0,2	0,4
2	25	16.000	2.800	0,1	0,3	16.000	2.800	0,1	0,3	16.000	2.600	0,1	0,3
2,5	20	16.000	3.500	0,25	0,5	16.000	3.500	0,25	0,5	16.000	3.300	0,25	0,5
2,5	40	10.000	1.200	0,1	0,2	10.000	1.200	0,1	0,2	10.000	1.100	0,1	0,2
3	12	20.000	5.200	0,3	0,5	20.000	5.200	0,3	0,5	20.000	5.200	0,3	0,5
3	20	16.000	4.200	0,3	0,5	16.000	4.200	0,3	0,5	16.000	3.900	0,3	0,5
3	25	12.000	3.200	0,3	0,5	12.000	3.200	0,3	0,5	12.000	3.000	0,3	0,5
3	30	10.000	2.600	0,3	0,5	10.000	2.600	0,3	0,5	10.000	2.400	0,3	0,5

Max cutting depth

Attention : sparks and/or flames can cause coolant fire. Be sure adequate fire prevention is available.
 1. Speeds and feeds are designed to be used in conjunction with small passes on a high speed & precision machine set-up.
 2. Do not use inflammable coolant. Using worn tools may generate sparks.
 3. Use compressed air or a high quality coolant with a low co-efficient of smoke emission.
 * Modified parameters

CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPS-LN-EBD

High speed milling



Vc		38 ~ 45 HRC				45 ~ 55 HRC				55 ~ 60 HRC			
		120 (m/min)				110 (m/min)				100 (m/min)			
R	l1 (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)
1,25	20	15.000	1.700	0,1	0,2	14.000	1.600	0,1	0,2	12.000	1.000	0,05	0,1
1,5	6	41.500	6.200	0,15	0,3	32.000	4.800	0,15	0,3	26.500	3.300	0,06	0,15
1,5	8	30.000	4.200	0,15	0,3	25.000	3.500	0,15	0,3	22.000	2.400	0,06	0,15
1,5	10	25.000	3.600	0,15	0,3	20.000	2.800	0,15	0,3	18.000	2.000	0,06	0,15
1,5	12	20.000	2.800	0,15	0,3	18.000	2.500	0,15	0,3	16.000	1.700	0,06	0,15
1,5	14	18.000	2.500	0,15	0,3	15.000	2.000	0,15	0,3	13.000	1.300	0,06	0,15
1,5	15	16.000	2.200	0,1	0,3	13.000	1.800	0,1	0,3	11.000	1.200	0,06	0,15
1,5	16	16.000	1.900	0,1	0,2	13.000	1.500	0,1	0,2	11.000	1.100	0,06	0,15
1,5	20	14.000	1.700	0,1	0,2	11.000	1.600	0,1	0,2	10.000	1.000	0,06	0,15
1,5	25	12.000	1.100	0,05	0,1	9.000	820	0,05	0,1	8.000	580	0,05	0,1
1,5	30	9.000	760	0,03	0,05	7.000	590	0,03	0,05	6.000	400	0,03	0,05
1,75	20	16.000	2.500	0,1	0,2	12.000	1.800	0,1	0,2	10.000	1.200	0,07	0,15
2	8	31.000	5.700	0,2	0,5	24.000	4.400	0,2	0,5	20.000	3.200	0,08	0,2
2	10	25.000	4.200	0,2	0,5	20.000	3.300	0,2	0,5	18.000	2.300	0,08	0,2
2	12	20.000	3.400	0,2	0,5	17.000	2.900	0,2	0,5	14.000	1.900	0,08	0,2
2	15	20.000	3.400	0,2	0,5	16.000	2.700	0,2	0,5	12.000	1.600	0,08	0,2
2	16	18.000	3.000	0,2	0,5	15.000	2.500	0,2	0,5	10.000	1.300	0,08	0,2
2	20	16.000	2.600	0,2	0,4	14.000	2.300	0,2	0,4	8.000	1.000	0,08	0,2
2	25	16.000	2.600	0,1	0,3	13.000	2.200	0,1	0,3	6.000	810	0,08	0,2
2,5	20	16.000	3.300	0,25	0,5	13.000	2.700	0,25	0,5	8.000	1.300	0,1	0,25
2,5	40	10.000	1.100	0,1	0,2	9.000	990	0,1	0,2	3.000	260	0,1	0,2
3	12	20.000	5.200	0,3	0,5	16.000	3.400	0,3	0,5	13.500	2.500	0,1	0,2
3	20	16.000	3.900	0,3	0,5	12.000	3.000	0,3	0,5	8.000	1.600	0,1	0,2
3	25	12.000	3.000	0,3	0,5	10.000	2.500	0,3	0,5	6.000	1.200	0,1	0,2
3	30	10.000	2.400	0,3	0,5	9.000	2.100	0,3	0,5	4.000	740	0,1	0,2




CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPS-CPR

Regular milling



Ø	α°	l1 (mm)	ap							ae	~ 45 HRC SKD61 • NAK55 • NAK80 • HPMI		45 ~ 55 HRC SKD61 • STAVAX • HPM38		55 ~ 65 HRC Hardened Steel	
			R0,05	R0,1	R0,2	R0,3	R0,5	R1	ap = 120%		ae = 120%	ap = 100%	ae = 100%	ap = 60%	ae = 80%	
			S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)		F (mm/min)	S (min ⁻¹)	F (mm/min)			
1	0°	4	0,01	0,02	0,04	0,05	-	-	0,300	23.000	1.300	20.000	1.050	17.000	755	
1	0°	4	-	-	-	-	-	-	0,300	23000	1300	20000	1050	17000	755	
1	0°	6	0,005	0,01	0,02	0,025	-	-	0,210	20.500	1.050	18.000	835	15.500	605	
1	0°	6	0,01	0,02	0,04	0,05	-	-	0,300	25.500	1.250	22.500	1.150	19.000	840	
1,5	0°	6	-	-	0,04	0,06	-	-	0,450	17.000	1.450	16.000	1.250	13.500	880	
1,5	0°	10	-	-	0,018	0,027	-	-	0,292	14.500	1.000	13.500	900	11.000	625	
1,5	0°	16	-	-	0,007	0,01	-	-	0,112	9.150	525	8.650	460	7.150	320	
2	0°	8	-	0,02	0,04	0,06	0,075	-	0,600	13.000	1.450	13.000	1.300	11.500	1.000	
2	0°	10	-	0,016	0,032	0,048	0,06	-	0,510	12.000	1.300	12.000	1.150	11.000	905	
2	0°	12	-	0,01	0,02	0,03	0,037	-	0,420	11.500	1.150	11.500	1.050	10.000	810	
3	0°	8	-	-	0,04	-	-	-	0,900	9.550	1.500	8.600	1.150	7.650	825	
3	0°	12	-	-	0,04	0,06	0,075	-	0,900	9.550	1.500	8.600	1.150	7.650	825	
3	0°	16	-	-	0,028	0,042	0,052	-	0,720	8.500	1.200	7.650	910	6.800	660	
4	0°	16	-	-	0,04	0,06	0,075	0,12	1,200	7.150	2.050	6.450	1.550	5.000	965	
4	0°	20	-	-	0,032	0,048	0,06	0,2	1,020	6.750	1.950	6.100	1.450	4.750	910	


1. Use a rigid and precise machine and holder.
2. When machining carbon steels or hardened steels, using MQL (Minimum Quantity Lubrication/mist coolant) is recommended.
3. The above condition shows an approximate standard for contouring operation (side milling) with a low machining load. If abnormal cutting sounds, vibration or chattering occur depending on the machinestype, cutting amount, rigidity of the machine or work holding condition etc., please adjust the speed, feed and the depth of cut.
4. Adjust the speed, feed rate, and depth of cut if chattering, vibration or abnormal grinding sounds occur.
5. Helical or ramp milling is recommended during the approach of a Z cut.
6. Adjust the speed, feed rate, and the depth of the cut according to the shape of the work, rigidity of the machine, and how the work is held.

CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPS-CPR


Side milling (Contour line finish)



Ø	α°	l1 (mm)	ap							ae	~ 45 HRC SKD61 • NAK55 • NAK80 • HPM1		45 ~ 55 HRC SKD61 • STAVAX • HPM38		55 ~ 65 HRC Hardened Steel	
			R0,05	R0,1	R0,2	R0,3	R0,5	R1	ap = 120%		ae = 120%	ap = 100%	ae = 100%	ap = 60%	ae = 80%	
			S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)								
1	0°	4	0,006	0,015	0,02	0,03	-	-	0,030	27.000	1.500	24.500	1.250	22.500	995	
1	0°	6	0,006	0,015	0,02	0,03	-	-	0,027	24.000	1.200	21.500	1.000	20.000	800	
1,5	0°	6	-	-	0,02	0,03	-	-	0,045	21.000	1.750	18.500	1.450	16.000	1.050	
1,5	0°	10	-	-	0,018	0,027	-	-	0,036	17.500	1.250	15.500	1.050	13.500	760	
1,5	0°	16	-	-	0,008	0,012	-	-	0,022	11.000	640	10.000	530	8.650	390	
2	0°	8	-	0,015	0,02	0,03	0,05	-	0,060	16.500	1.850	16.000	1.600	15.000	1.350	
2	0°	10	-	0,015	0,02	0,03	0,05	-	0,060	15.500	1.650	15.500	1.450	14.500	1.200	
2	0°	12	-	0,015	0,02	0,03	0,05	-	0,054	14.500	1.500	14.500	1.300	13.500	1.050	
3	0°	8	-	-	0,02	-	-	-	0,080	12.000	2.000	11.000	1.400	10.000	1.100	
3	0°	12	-	-	0,02	0,03	0,05	-	0,080	12.000	2.000	11.000	1.400	10.000	1.100	
3	0°	16	-	-	0,02	0,03	0,05	-	0,080	10.500	1.600	9.600	1.150	9.000	875	
4	0°	16	-	-	0,02	0,03	0,05	0,08	0,080	7.900	2.500	7.150	2.050	6.450	1.450	
4	0°	20	-	-	0,02	0,03	0,05	0,08	0,080	7.450	2.400	6.750	1.950	6.100	1.350	

Approximate offset (mm)

R	Target surface roughness (µm)													
	0,1	0,25	0,5	0,75	1	1,25	1,5	1,75	2	2,5	3	3,5	4	5
R 0,05	0,006	0,01	0,014	0,017	0,02	0,022	0,024	0,026	0,028	-	-	-	-	-
R 0,1	0,009	0,014	0,02	0,024	0,028	0,032	0,035	0,037	0,04	0,045	0,049	-	-	-
R 0,2	0,012	0,02	0,028	0,035	0,04	0,045	0,049	0,053	0,057	0,063	0,07	0,075	0,08	0,9
R 0,3	0,015	0,025	0,035	0,042	0,049	0,055	0,06	0,065	0,07	0,077	0,085	0,092	0,098	0,11
R 0,5	0,02	0,032	0,045	0,055	0,065	0,07	0,078	0,084	0,09	0,1	0,11	0,118	0,125	0,141
R 1	0,028	0,045	0,063	0,078	0,09	0,1	0,11	0,118	0,125	0,142	0,155	0,168	0,18	0,2



CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPL-LN-EBD

Standard milling


R	l1 (mm)	Cu				< 32 HRC				32 - 41 HRC				42 - 50 HRC			
		S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)
0,15	0,5	32.000	600	0,020	0,030	32.000	400	0,010	0,015	32.000	300	0,010	0,015	32.000	300	0,005	0,005
0,15	1	32.000	450	0,020	0,030	32.000	300	0,010	0,015	32.000	200	0,010	0,015	32.000	200	0,005	0,005
0,2	1	32.000	600	0,025	0,050	32.000	400	0,015	0,025	32.000	300	0,015	0,020	32.000	300	0,010	0,010
0,2	2	27.000	450	0,025	0,050	27.000	300	0,015	0,025	27.000	200	0,015	0,020	27.000	200	0,010	0,010
0,25	1	32.000	750	0,040	0,050	32.000	500	0,020	0,025	32.000	400	0,020	0,020	32.000	400	0,010	0,010
0,25	2	32.000	600	0,040	0,050	32.000	400	0,020	0,025	32.000	300	0,020	0,020	32.000	300	0,010	0,010
0,25	3	27.000	450	0,040	0,050	27.000	300	0,020	0,025	27.000	200	0,020	0,020	27.000	200	0,010	0,010
0,25	4	27.000	450	0,040	0,050	27.000	300	0,020	0,025	27.000	200	0,020	0,020	27.000	200	0,010	0,010
0,3	1	32.000	900	0,045	0,120	32.000	600	0,030	0,060	32.000	500	0,030	0,050	32.000	500	0,030	0,030
0,3	2	32.000	675	0,045	0,120	32.000	450	0,030	0,060	32.000	300	0,030	0,050	32.000	300	0,030	0,030
0,3	3	30.000	375	0,045	0,120	25.000	250	0,030	0,060	24.000	200	0,030	0,050	24.000	200	0,030	0,030
0,3	4	30.000	375	0,045	0,120	25.000	250	0,030	0,060	24.000	200	0,030	0,040	24.000	200	0,030	0,030
0,3	6	25.000	225	0,045	0,120	20.000	150	0,030	0,060	20.000	150	0,030	0,040	20.000	150	0,020	0,020
0,4	2	27.000	675	0,060	0,160	23.000	450	0,040	0,080	21.000	300	0,040	0,060	21.000	300	0,040	0,040
0,4	4	27.000	675	0,060	0,160	23.000	450	0,040	0,080	21.000	300	0,040	0,060	21.000	300	0,040	0,040
0,4	6	24.000	375	0,060	0,120	21.000	250	0,040	0,060	19.000	200	0,040	0,050	19.000	200	0,020	0,025
0,5	2,5	28.000	900	0,075	0,200	25.000	600	0,050	0,100	21.000	400	0,050	0,080	21.000	400	0,050	0,050
0,5	3	28.000	750	0,075	0,200	25.000	500	0,050	0,100	21.000	300	0,050	0,080	21.000	300	0,050	0,050
0,5	4	28.000	750	0,075	0,200	25.000	500	0,050	0,100	21.000	300	0,050	0,080	21.000	300	0,050	0,050
0,5	5	21.000	450	0,075	0,200	19.000	300	0,050	0,100	16.000	200	0,050	0,080	16.000	200	0,050	0,050
0,5	6	21.000	450	0,075	0,200	19.000	300	0,050	0,100	16.000	200	0,050	0,080	16.000	200	0,050	0,050
0,5	8	21.000	450	0,075	0,150	19.000	300	0,050	0,075	16.000	200	0,050	0,060	16.000	200	0,030	0,030
0,5	10	18.000	300	0,060	0,120	17.000	200	0,030	0,050	14.000	150	0,030	0,040	14.000	150	0,010	0,015
0,5	12	18.000	300	0,060	0,120	17.000	200	0,030	0,050	14.000	150	0,030	0,040	14.000	150	0,010	0,015
0,75	4	20.000	900	0,120	0,300	15.000	600	0,080	0,150	12.000	500	0,080	0,120	12.000	300	0,080	0,100
0,75	8	17.000	450	0,120	0,300	15.000	300	0,080	0,150	12.000	250	0,080	0,120	12.000	250	0,080	0,100
1	6	16.500	1.050	0,150	0,560	16.500	700	0,100	0,280	13.500	500	0,100	0,280	13.500	500	0,100	0,200
1	8	16.500	1.050	0,150	0,560	16.500	700	0,100	0,280	13.500	500	0,100	0,280	13.500	500	0,100	0,200
1	10	14.000	750	0,150	0,560	13.000	500	0,100	0,280	10.000	300	0,100	0,280	10.000	300	0,100	0,200
1	12	14.000	750	0,150	0,560	13.000	500	0,100	0,280	10.000	300	0,100	0,280	10.000	300	0,100	0,200
1	14	14.000	750	0,150	0,560	13.000	500	0,100	0,280	10.000	300	0,100	0,280	10.000	300	0,100	0,200
1	16	14.000	750	0,150	0,420	13.000	500	0,100	0,210	10.000	300	0,100	0,180	10.000	300	0,060	0,100
1	20	11.000	375	0,150	0,420	10.000	250	0,100	0,210	8.000	200	0,100	0,180	8.000	200	0,060	0,100
1	25	11.000	375	0,150	0,420	10.000	250	0,100	0,210	8.000	200	0,100	0,180	8.000	200	0,060	0,100
1,5	8	12.000	900	0,200	0,840	9.500	600	0,150	0,420	7.500	400	0,150	0,360	7.500	400	0,150	0,300
1,5	10	12.000	900	0,200	0,840	9.500	600	0,150	0,420	7.500	400	0,150	0,360	7.500	400	0,150	0,300
1,5	16	10.000	450	0,200	0,840	8.500	300	0,150	0,420	6.500	250	0,150	0,360	6.500	250	0,150	0,300
1,5	20	10.000	450	0,200	0,840	8.500	300	0,150	0,420	6.500	250	0,150	0,360	6.500	250	0,150	0,300
2	10	9.000	900	0,500	1,280	7.500	600	0,200	0,640	6.000	400	0,200	0,600	6.000	400	0,200	0,400
2	16	9.000	900	0,500	1,280	7.500	600	0,200	0,640	6.000	400	0,200	0,600	6.000	400	0,200	0,400
2	20	7.000	600	0,500	1,280	6.000	400	0,200	0,640	5.000	250	0,200	0,600	5.000	250	0,200	0,400
2	25	7.000	600	0,500	1,280	6.000	400	0,200	0,640	5.000	250	0,200	0,600	5.000	250	0,200	0,400
2	30	7.000	600	0,400	1,280	6.000	400	0,200	0,640	5.000	250	0,200	0,560	5.000	250	0,120	0,200
3	10	7.000	1.500	0,750	2,400	5.500	1.000	0,300	1,200	4.500	800	0,300	0,960	4.500	800	0,300	0,600
3	12	7.000	1.500	0,750	2,400	5.500	1.000	0,300	1,200	4.500	800	0,300	0,960	4.500	800	0,300	0,600
3	20	7.000	1.200	0,750	2,400	5.500	800	0,300	1,200	4.500	600	0,300	0,960	4.500	600	0,300	0,600
3	30	5.000	600	0,750	2,400	4.000	400	0,300	1,200	4.000	300	0,300	0,960	4.000	300	0,300	0,600

CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPL-LN-EBD

High speed milling



R	l1 (mm)	Cu				< 32 HRC				32 - 41 HRC				42 - 50 HRC			
		S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)	S (min ⁻¹)	F (mm/min)	ap (mm)	pf (mm)
0,15	0,5	50.000	750	0,0075	0,020	50.000	620	0,005	0,010	50.000	600	0,005	0,010	50.000	600	0,005	0,010
0,15	1	50.000	730	0,0075	0,020	50.000	600	0,005	0,010	50.000	570	0,005	0,010	50.000	570	0,005	0,010
0,2	1	50.000	1.090	0,015	0,040	50.000	900	0,020	0,010	50.000	850	0,010	0,020	50.000	850	0,010	0,020
0,2	2	50.000	850	0,015	0,040	50.000	700	0,020	0,010	50.000	660	0,010	0,020	50.000	660	0,010	0,020
0,25	1	50.000	1.420	0,0225	0,045	50.000	1.100	0,015	0,030	50.000	1.050	0,010	0,030	50.000	1.050	0,015	0,030
0,25	2	50.000	1.400	0,0225	0,045	50.000	1.000	0,015	0,030	50.000	950	0,010	0,030	50.000	950	0,015	0,030
0,25	3	50.000	1.190	0,015	0,040	48.000	900	0,010	0,020	48.000	850	0,010	0,020	48.000	850	0,010	0,020
0,25	4	45.000	1.000	0,015	0,020	43.000	600	0,010	0,010	43.000	570	0,010	0,010	43.000	570	0,010	0,010
0,3	1	50.000	1.660	0,045	0,100	50.000	1.400	0,030	0,050	50.000	1.300	0,030	0,050	50.000	1.300	0,030	0,050
0,3	2	50.000	1.600	0,045	0,100	50.000	1.300	0,030	0,050	50.000	1.200	0,030	0,050	50.000	1.200	0,030	0,050
0,3	3	50.000	1.550	0,030	0,060	50.000	1.200	0,020	0,030	50.000	1.100	0,020	0,030	50.000	1.100	0,020	0,030
0,3	4	50.000	1.200	0,015	0,040	40.000	900	0,010	0,020	40.000	850	0,010	0,020	40.000	850	0,010	0,020
0,3	6	30.000	720	0,015	0,040	26.000	600	0,010	0,020	26.000	570	0,010	0,020	25.000	540	0,010	0,020
0,4	2	50.000	2.200	0,060	0,160	50.000	2.000	0,040	0,080	50.000	1.900	0,040	0,080	50.000	1.900	0,040	0,080
0,4	4	50.000	1.680	0,060	0,160	40.000	1.200	0,040	0,080	40.000	1.100	0,040	0,080	40.000	1.100	0,040	0,080
0,4	6	32.000	1.260	0,045	0,100	30.000	800	0,030	0,050	30.000	760	0,030	0,050	30.000	760	0,030	0,050
0,5	2,5	50.000	3.270	0,075	0,200	50.000	3.400	0,050	0,100	50.000	3.200	0,050	0,100	50.000	3.200	0,050	0,100
0,5	3	50.000	3.060	0,075	0,200	45.000	3.200	0,050	0,100	45.000	3.000	0,050	0,100	45.000	3.000	0,050	0,100
0,5	4	50.000	3.000	0,075	0,200	40.000	3.000	0,050	0,100	40.000	2.850	0,050	0,100	40.000	2.850	0,050	0,100
0,5	5	47.000	2.870	0,075	0,200	36.000	2.300	0,050	0,100	36.000	2.100	0,050	0,100	36.000	2.100	0,050	0,100
0,5	6	43.000	2.600	0,075	0,200	30.000	2.000	0,050	0,100	30.000	1.900	0,050	0,100	30.000	1.900	0,050	0,100
0,5	8	27.000	2.000	0,075	0,150	26.000	1.600	0,050	0,100	26.000	1.500	0,050	0,100	26.000	1.500	0,050	0,100
0,5	10	24.000	1.400	0,015	0,040	22.000	1.100	0,010	0,020	22.000	1.000	0,010	0,020	21.000	950	0,010	0,020
0,5	12	24.000	1.400	0,015	0,040	22.000	1.100	0,010	0,020	22.000	1.000	0,010	0,020	21.000	950	0,010	0,020
0,75	4	42.000	4.110	0,150	0,300	40.000	3.900	0,075	0,150	40.000	3.700	0,075	0,150	40.000	3.700	0,075	0,1005
0,75	8	30.000	2.650	0,150	0,300	24.000	2.300	0,075	0,150	24.000	2.100	0,075	0,150	24.000	2.100	0,075	0,1005
1	6	38.000	4.000	0,200	0,400	36.000	3.000	0,100	0,200	36.000	2.800	0,100	0,200	34.000	2.600	0,100	0,200
1	8	27.000	3.360	0,200	0,400	25.000	2.600	0,100	0,200	25.000	2.400	0,100	0,200	23.000	2.200	0,100	0,200
1	10	22.000	3.050	0,200	0,400	20.000	2.400	0,100	0,200	20.000	2.200	0,100	0,200	19.000	2.000	0,100	0,200
1	12	16.000	2.580	0,200	0,400	16.000	2.000	0,100	0,200	16.000	1.900	0,100	0,200	15.000	1.700	0,100	0,200
1	14	15.000	2.400	0,200	0,300	15.000	1.800	0,100	0,200	15.000	1.700	0,100	0,200	14.000	1.500	0,100	0,200
1	16	14.000	2.200	0,200	0,200	14.000	1.700	0,100	0,100	14.000	1.600	0,100	0,100	13.000	1.400	0,100	0,100
1	20	12.000	1.200	0,100	0,200	12.000	1.200	0,050	0,100	11.000	1.100	0,050	0,100	10.000	1.000	0	0,100
1	25	12.000	1.200	0,100	0,200	12.000	1.200	0,050	0,100	11.000	1.100	0,050	0,100	10.000	1.000	0	0,100
1,5	8	32.000	4.600	0,300	0,600	30.000	4.500	0,150	0,300	30.000	4.200	0,150	0,300	25.000	3.500	0,150	0,300
1,5	10	28.000	4.000	0,300	0,600	25.000	3.800	0,150	0,300	25.000	3.600	0,150	0,300	20.000	2.800	0,150	0,300
1,5	16	20.000	2.600	0,250	0,400	16.000	2.000	0,100	0,200	16.000	1.900	0,100	0,200	13.000	1.500	0,100	0,200
1,5	20	16.000	2.200	0,250	0,400	14.000	1.800	0,100	0,200	14.000	1.700	0,100	0,200	11.000	1.300	0,100	0,200
2	10	25.000	4.500	0,400	1,000	25.000	4.500	0,200	0,500	25.000	4.200	0,200	0,500	20.000	3.300	0,200	0,500
2	16	20.000	3.460	0,400	0,600	18.000	3.200	0,200	0,500	18.000	3.000	0,200	0,500	14.000	2.300	0,200	0,500
2	20	18.000	3.000	0,400	0,500	16.000	2.800	0,200	0,400	16.000	2.600	0,200	0,400	12.000	1.900	0,200	0,400
2	25	18.000	3.000	0,250	0,600	16.000	2.800	0,100	0,300	16.000	2.600	0,100	0,300	12.000	1.900	0,100	0,300
2	30	16.000	2.850	0,250	0,400	14.000	2.400	0,100	0,200	14.000	2.200	0,100	0,200	11.000	1.700	0,100	0,200
3	10	22.000	5.900	0,750	1,250	20.000	5.400	0,300	0,500	20.000	5.000	0,300	0,500	15.000	3.750	0,300	0,500
3	12	22.000	5.900	0,750	1,250	20.000	5.400	0,300	0,500	20.000	5.000	0,300	0,500	15.000	3.750	0,300	0,500
3	20	18.000	4.400	0,750	1,250	16.000	4.200	0,300	0,500	16.000	3.900	0,300	0,500	12.000	2.900	0,300	0,500
3	30	10.000	3.200	0,600	1,25	10.000	2.600	0,3	0,5	10.000	2.400	0,3	0,5	8.000	1.900	0,3	0,5

CUTTING CONDITIONS

Milling | Endmills | Cutting conditions


EPL-CPR

Regular milling

Hardened steel, pre-Hardened steel															
Ø	φ°	l1	Max. cutting depth						< 45 HRC ap=120% ae=120%		45 - 55 HRC ap=100% ae=120%		55 - 65 HRC ap=60% ae=80%		
			R0,1	R0,2	R0,3	ap	R1	R2	ae	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)
1	0°	4	0,020	0,04	0,050	-	-	-	0,300	23.000	1.300	20.000	1.050	17.000	755
1	0°	6	0,010	0,02	0,025	-	-	-	0,210	20.500	1.050	18.000	835	15.500	605
1	0°	8	0,006	0,012	0,015	-	-	-	0,180	18.000	780	15.500	650	13.500	470
1	0°	10	-	0,008	0,010	-	-	-	0,090	16.500	650	14.500	530	12.500	380
2	0°	6	-	0,040	-	0,075	-	-	0,600	15.000	1680	15.000	1500	11.500	1.000
2	0°	8	-	0,040	-	0,075	-	-	0,600	13.000	1.450	13.000	1.300	11.500	1.000
2	0°	10	-	0,032	-	0,060	-	-	0,510	12.000	1.300	12.000	1.150	11.000	905
2	0°	12	-	0,020	-	0,037	-	-	0,420	11.500	1.150	11.500	1.050	10.000	810
2	0°	16	-	0,012	-	0,022	-	-	0,360	10.000	900	10.000	800	8.900	630
2	0,9°	20	-	-	-	0,052	-	-	0,540	13.000	1.300	13.000	1.150	11.500	910
2	0,9°	30	-	-	-	0,030	-	-	0,240	11.500	1.050	11.500	920	10.000	720
3	0°	6	-	0,044	-	0,083	-	-	0,900	11.700	2000	10.500	1530	7.650	825
3	0°	8	-	0,040	-	0,075	-	-	0,900	9.550	1.500	8.600	1.150	7.650	825
3	0°	10	-	0,040	-	0,075	-	-	0,900	9.550	1.500	8.600	1.150	7.650	825
3	0°	12	-	0,040	-	0,075	-	-	0,900	9.550	1.500	8.600	1.150	7.650	825
3	0°	16	-	0,028	-	0,052	-	-	0,720	8.500	1.200	7.650	910	6.800	660
3	0,9°	20	-	-	-	0,070	0,09	-	0,900	9.950	1.500	8.950	1.150	7.950	830
3	0,9°	30	-	-	-	0,050	0,07	-	0,810	9.550	1.350	8.600	1.000	7.650	745
3	0,9°	40	-	-	-	0,040	0,05	-	0,522	8.900	1.150	8.000	890	7.150	650
3	1,4°	20	-	-	-	0,090	0,13	-	0,900	9.950	1.690	8.950	1.350	7.950	950
3	1,4°	30	-	-	-	0,070	0,13	-	0,810	9.550	1.550	8.600	1.200	7.650	850
3	1,4°	40	-	-	-	-	0,13	-	0,522	8.900	1.350	8.000	1.040	7.150	700
4	0°	10	-	-	-	-	0,13	-	1,320	8.750	2.770	7.900	2080	5.750	1.250
4	0°	12	-	-	-	0,075	0,12	-	1,200	8.350	2.400	7.500	1800	5.400	1.080
4	0°	16	-	-	-	0,075	0,12	-	1,200	7.150	2.050	6.450	1.550	5.000	965
4	0°	20	-	-	-	0,060	0,2	-	1,020	6.750	1.950	6.100	1.450	4.750	910
4	0,9°	30	-	-	-	0,050	0,09	-	1,120	7.550	1.500	7.150	1.300	6.400	950
4	0,9°	40	-	-	-	0,040	0,09	-	0,900	7.200	1.350	6.750	1.150	5.950	850
4	0,9°	50	-	-	-	0,030	0,07	-	0,810	7.150	1.300	6.600	1.050	5.800	750
4	0,9°	60	-	-	-	-	0,05	-	0,522	6.800	1.150	6.400	950	5.600	700
4	1,4°	30	-	-	-	0,070	0,13	-	1,120	7.550	1.500	7.150	1.300	6.400	950
4	1,4°	40	-	-	-	0,060	0,13	-	0,900	7.200	1.400	6.750	1.150	5.950	850
6	0°	12	-	-	-	0,083	0,13	-	1,980	6.130	2.900	5.550	2200	3.850	900
6	0°	16	-	-	-	0,075	0,12	-	1,800	5.000	2.170	4.540	1630	3.600	800
6	0°	20	-	-	-	0,075	0,12	-	1,800	5.000	2.170	4.540	1630	3.350	700
6	0°	25	-	-	-	0,075	0,12	-	1,800	5.000	2.170	4.540	1630	3.180	650
6	0,9°	50	-	-	-	0,030	0,13	-	1,680	5.300	1.100	5.050	950	4.250	700
6	0,9°	60	-	-	-	0,030	0,09	-	1,200	5.150	1.030	4.900	900	3.950	600
6	0,9°	70	-	-	-	0,020	0,07	-	1,200	4.950	950	4.750	800	3.800	550
6	0,9°	80	-	-	-	-	0,07	-	1,020	4.750	850	4.500	720	3.750	500
8	0,9°	60	-	-	-	0,070	0,13	-	2,160	4.350	950	4.000	800	3.800	650
8	0,9°	80	-	-	-	0,050	0,09	0,2	1,920	4.150	830	3.800	700	3.550	550

Offset

roughness (µm)													
Corner Radius R (mm)	0,10	0,25	0,75	1,00	1,25	1,50	1,75	2,00	2,50	3,00	3,25	4,00	5,00
R 0,1	0,009	0,014	0,024	0,028	0,032	0,035	0,037	0,040	0,045	0,049	-	-	-
R 0,2	0,012	0,020	0,035	0,040	0,045	0,049	0,053	0,057	0,063	0,070	0,075	0,080	0,900
R 0,3	0,015	0,025	0,042	0,049	0,055	0,060	0,065	0,070	0,077	0,085	0,092	0,098	0,110
R 0,5	0,020	0,032	0,055	0,065	0,070	0,078	0,084	0,090	0,100	0,110	0,118	0,125	0,141
R 1	0,028	0,045	0,078	0,090	0,100	0,110	0,111	0,125	0,142	0,155	0,168	0,180	0,200



CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

EPL-CPR

Side milling (Contour line finish)



Hardened steel, pre-Hardened steel


D	φ°	l1	Max. cutting depth							< 45 HRC ap=120% ae=120%		45 - 55 HRC ap=100% ae=120%		55 - 65 HRC ap=60% ae=80%	
			R0,1	R0,2	R0,3	ap	R1	R2	ae	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)	S (min ⁻¹)	F (mm/min)
1	0°	4	0,015	0,020	0,03	-	-	-	0,030	27.000	1.500	24.500	1.250	22.500	995
1	0°	6	0,015	0,020	0,03	-	-	-	0,027	24.000	1.200	21.500	1.000	20.000	800
1	0°	8	0,009	0,012	0,018	-	-	-	0,021	21.000	950	19.000	790	17.500	620
1	0°	10	-	0,008	0,012	-	-	-	0,015	19.500	770	17.500	640	16.500	505
2	0°	6	-	0,020	-	0,05	-	-	0,060	16.500	1850	16.000	1.600	15.000	1.350
2	0°	8	-	0,020	-	0,05	-	-	0,060	16.500	1850	16.000	1.600	15.000	1.350
2	0°	10	-	0,020	-	0,05	-	-	0,060	15.500	1.650	15.500	1.450	14.500	1.200
2	0°	12	-	0,020	-	0,05	-	-	0,054	14.500	1.500	14.500	1.300	13.500	1.050
2	0°	16	-	0,012	-	0,03	-	-	0,042	13.000	1.150	12.500	1.000	12.000	830
2	0,9°	20	0,050	-	-	-	-	-	0,060	16.500	1.650	16.000	1.450	15.000	1.200
2	0,9°	30	0,040	-	-	-	-	-	0,048	14.500	1.300	14.500	1.150	13.500	950
3	0°	6	-	0,020	-	0,05	-	-	0,080	12.600	2.100	11.400	1.500	10.000	1.100
3	0°	8	-	0,020	-	0,05	-	-	0,080	12.000	2.000	11.000	1.400	10.000	1.100
3	0°	10	-	0,020	-	0,05	-	-	0,080	12.000	2.000	11.000	1.400	10.000	1.100
3	0°	12	-	0,020	-	0,05	-	-	0,080	12.000	2.000	11.000	1.400	10.000	1.100
3	0°	16	-	0,020	-	0,05	-	-	0,080	10.500	1.600	9.600	1.150	9.000	875
3	0,9°	20	0,050	0,090	-	-	-	-	0,080	12.500	2.000	11.500	1.450	10.500	1.100
3	0,9°	30	0,050	0,070	-	-	-	-	0,080	12.000	1.800	11.000	1.300	10.000	985
3	0,9°	40	0,045	0,070	-	-	-	-	0,064	11.000	1.550	10.000	1.100	9.450	860
3	1,4°	20	0,090	0,130	-	-	-	-	0,080	12.500	2.250	11.500	1.750	10.500	1.250
3	1,4°	30	0,070	0,130	-	-	-	-	0,080	12.000	2.050	11.000	1.550	10.000	1.100
3	1,4°	40	-	0,130	-	-	-	-	0,064	11.000	1.750	10.000	1.300	9.450	950
4	0°	10	-	-	-	-	0,08	-	0,080	8.300	2.700	7.550	2.200	7.600	1.650
4	0°	12	-	-	-	-	0,08	-	0,080	7.900	2.500	7.150	2.050	7.200	1.550
4	0°	16	-	-	-	-	0,08	-	0,080	7.900	2.500	7.150	2.050	6.450	1.450
4	0°	20	-	-	-	0,05	0,08	-	0,080	7.450	2.400	6.750	1.950	6.100	1.350
4	0,9°	30	-	-	-	0,050	0,090	-	0,106	9.950	1.900	9.150	1.450	8.350	1.100
4	0,9°	40	-	-	-	0,040	0,090	-	0,106	9.600	1.750	8.800	1.350	8.050	1.000
4	0,9°	50	-	-	-	0,030	0,070	-	0,085	9.500	1.600	8.500	1.200	7.750	850
4	0,9°	60	-	-	-	-	0,050	-	0,085	9.150	1.450	8.350	1.100	7.550	750
4	1,4°	30	-	-	-	0,070	0,130	-	0,106	9.950	2.100	9.150	1.650	8.350	1.100
4	1,4°	40	-	-	-	0,060	0,130	-	0,106	9.600	1.950	8.800	1.500	8.050	950
6	0°	12	-	-	-	0,05	0,08	-	0,100	5.500	2.650	5.050	2.150	5.050	1.800
6	0°	16	-	-	-	0,05	0,08	-	0,100	5.250	2.500	4.750	2.050	4.750	1.750
6	0°	20	-	-	-	0,05	0,08	-	0,100	5.250	2.500	4.750	2.050	4.500	1.750
6	0°	25	-	-	-	0,05	0,08	-	0,100	4.950	2.350	4.500	1.950	4.250	1.600
6	0,9°	50	-	-	-	0,030	0,130	-	0,130	7.450	1.700	6.900	1.400	6.350	950
6	0,9°	60	-	-	-	0,030	0,090	-	0,130	7.200	1.600	6.700	1.300	6.150	850
6	0,9°	70	-	-	-	0,020	0,070	-	0,130	7.050	1.500	6.500	1.200	5.900	750
6	0,9°	80	-	-	-	-	0,070	-	0,100	6.900	1.400	6.350	1.100	5.850	700
8	0,9°	60	-	-	-	0,070	0,130	-	0,192	6.350	1.550	5.950	1.250	5.550	900
8	0,9°	80	-	-	-	0,050	0,090	0,2	0,160	5.950	1.300	5.550	1.050	5.150	

Zeilensprung



Target surface roughness (μm)

Eckenradius R (mm)	0,10	0,25	0,75	1,00	1,25	1,50	1,75	2,00	2,50	3,00	3,25	4,00	5,00
R 0,1	0,009	0,014	0,024	0,028	0,032	0,035	0,037	0,040	0,045	0,049	-	-	-
R 0,2	0,012	0,020	0,035	0,040	0,045	0,049	0,053	0,057	0,063	0,070	0,075	0,080	0,900
R 0,3	0,015	0,025	0,042	0,049	0,055	0,060	0,065	0,070	0,077	0,085	0,092	0,098	0,110
R 0,5	0,020	0,032	0,055	0,065	0,070	0,078	0,084	0,090	0,100	0,110	0,118	0,125	0,141
R 1	0,028	0,045	0,078	0,090	0,100	0,110	0,111	0,125	0,142	0,155	0,168	0,180	0,200



SWEDEN

Branch office of OSG SCANDINAVIA
Abrahams Gränd 8
295 35 Bromölla
Sweden
Tel: +46 40 41 22 55
osg@osg-scandinavia.com

OSG SCANDINAVIA

(For Scandinavian countries)
Langebjergvaenget 16
4000 Roskilde
Denmark
Tel: +45 46 75 65 55
osg@osg-scandinavia.com

OSG NETHERLANDS

Bedrijfsweg 5
3481 MG Harmelen
The Netherlands
Tel: +31 348 44 2764
Fax: +31 348 44 2144
info@osg-nl.com

OSG UK

Shelton house, 5 Bentalls
Pipps Hill Ind Est, Basildon Essex SS14 3BY
United Kingdom
Tel: +44 1268 567660
Fax: +44 1268 567661
sales@osg-uk.com

OSG EUROPE LOGISTICS

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord
Belgium
Tel: +32 10 23 05 07
Fax: +32 10 23 05 51
info@osgeurope.com

OSG BELUX

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord
Belgium
Tel: +32 10 23 05 11
Fax: +32 10 23 05 31
info@osg-belgium.com

OSG IBÉRICA

Bekolarra 4
E - 01010 Vitoria-Gasteiz
Spain
Tel: +34 945 242 400
Fax: +34 945 228 883
osg.iberica@osg-ib.com


OSG FRANCE

Parc Icade, Paris Nord 2
Immeuble "Le Rimbaud"
22 Avenue des Nations
CS66191 - 93420 Villepinte
France
Tel: +33 1 49 90 10 10
Fax: +33 1 49 90 10 15
sales@osg-france.com

OSG ITALY

Via Ferrero, 65 A/B
I - 10098 Rivoli
Italian
Tel: +39 0117705211
Fax: +39 0117705215
info@osg-italia.it





CZECH REPUBLIC, SLOVAKIA, HUNGARY

OSG Europe Logistics S.A.
Slovakia, organizačná zložka
Račianska 22/A, Bratislava 831 02
Slovakia
Tel.: +421 24 32 91 295
info@osgeurope.com

OSG POLAND

ul. Spółdzielcza 57
05-074 Halinów
Polska
Tel: +22 760 82 71
Mob. +48 570 677 711
osg@osg-poland.com

OSG RUSSIA

Butlerova street, 17B, office 5069
117342 Moscow
Russia
Tel: +7 (495) 150 41 54
info@osg-russia.com

ROMSAN INTERNATIONAL CO. SRL

Reprezentant Exclusiv OSG
25C, Bucuresti-Magurele Street
051431 Bucuresti
România
Tel: +40 21 322 07 47
Fax: +40 21 321 56 00
romsan.int@romsan.ro

OSG TURKEY

Rami Kişla Cad.No:56 Eyüp
Istanbul 34056
Turkey
Tel: +90 212 565 24 00
Fax: +90 212 565 44 00
info@osg-turkey.com

Vischer & Bolli AG

Machining and Workholding
Im Schossacher 17
CH-8600 Dübendorf
Schweiz
Tel.: +41 44 802 15 15
Fax: +41 44 802 15 95
info@vb-tools.com

OSG GERMANY

Karl-Ehmann-Str. 25
D - 73037 Göppingen
Germany
Tel: +49 7161 6064 - 0
Fax: +49 7161 6064 - 444
info@osg-germany.de



shaping your dreams

OSG EUROPE LOGISTICS

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord - Belgium
Tel: +32 10 23 05 07
Fax: +32 10 23 05 51
info@osgeurope.com

OSG BELUX

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord - Belgium
Tel: +32 10 23 05 11
Fax: +32 10 23 05 31
info@osg-belgium.com

OSG FRANCE

Parc Icade, Paris Nord 2
Immeuble "Le Rimbaud"
22 Avenue des Nations
CS66191 - 93420 Villepinte - France
Tel: +33 1 49 90 10 10
Fax: +33 1 49 90 10 15
sales@osg-france.com

OSG NETHERLANDS

Bedrijfsweg 5 - 3481 MG Harmelen
Tel: +31 348 44 2764
Fax: +31 348 44 2144
info@osg-nl.com

OSG UK

Shelton house, 5 Bentalls
Pipps Hill Ind Est, Basildon Essex SS14 3BY
Tel: +44 1268 567 660
Fax: +44 1268 567 661
uk_sales@osg-uk.com

CZECH, SLOVAKIA, HUNGARY

OSG Europe Logistics S.A.
Slovakia organizacna zlozka
Racianská 22/A, SK-83102 Bratislava
Slovakia
Tel. +421 24 32 91 295
Orders-osgsvk@osgeurope.com

OSG POLAND Sp. z.o.o.

Spółdzielcza 57
05-074 Halinów - Poland
Tel: +22 760 82 71
Fax: +22 760 82 71
osg@osg-poland.com

OSG GERMANY

Karl-Ehmann-Str. 25
D - 73037 Göppingen - Germany
Tel: +49 7161 6064 - 0
Fax: +49 7161 6064 - 444
info@osg-germany.de

OSG SCANDINAVIA

(For Scandinavian countries)
Langebjergvaenget 16
4000 Roskilde - Denmark
Tel: +45 46 75 65 55
Fax: +45 46 75 67 00
osg@osg-scandinavia.com

SWEDEN

Branch office of OSG SCANDINAVIA
Abrahams Gränd 8
295 35 Bromölla - Sweden
Tel: +46 40 41 22 55
Fax: +46 40 41 32 55
osg@osg-scandinavia.com

OSG IBERICA

Bekolarra 4
E - 01010 Vitoria-Gasteiz - Spain
Tel: +34 945 242 400
Fax: +34 945 228 883
osg.iberica@osg-ib.com

RUSSIA

Butlerova street, 17B, office 5069
117342 Moscow - Russia
Tel: +7 (495) 150 41 54
info@osg-russia.com

OSG TURKEY

Rami Kişla Cad.No:56 Eyüp
Istanbul 34056 - Turkey
Tel:+90 212 565 24 00
Fax: +90 212 565 44 00
info@osg-turkey.com

ROMSAN INTERNATIONAL CO. SRL

Reprezentant Exclusiv OSG
Bucharest Magurele Road Nr. 25C
051431 Bucuresti, District 5 - România
Tel: +40 21 322 07 47
Fax: +40 21 321 56 00
romsan.int@romsan.ro

AUSTRIA

Branch office of OSG GERMANY
Messestraße 11
A-6850 Dornbirn
Tel: +49 7161 6064-0
Fax: +49 7161 6064-444
info@osg-germany.de

OSG ITALIA

Via Ferrero, 65 A/B
I - 10098 Rivoli - Italy
Tel: +39 0117705211
Fax: +39 0117705215
info@osg-italia.it

Vischer & Bolli AG

Machining and Workholding
Im Schossacher 17
CH-8600 Dübendorf
T +41 44 802 15 15
F +41 44 802 15 95
info@vb-tools.com

OSG EUROPE LOGISTICS S.A.

12/2020 - All rights reserved. © OSG Europe 2020.

The contents of this catalogue are provided to you for viewing only. They are not intended for reproduction either in part or in whole in this or other medium. They cannot be copied, used to create derivation work or used for any reason, by means without the express, written permission of the copyright owner. If prices are stated, they are netto unit-prices and any eventual tax(es) have to be added. The company is not responsible for any printing error in technical, price and/or any other data.

Tool specifications subject to change without notice.

www.osgeurope.com